

tecno^{plus} SATIN

CARTE PER STAMPE DI PREGIO - FINE PAPERS

CARTE PATINATE SENZA LEGNO - COATED WOODFREE PAPER (CWF)



Grammatura Substance	ISO 536	g/m ²	90	100	115	130	150	170	200	250
Spessore Caliper	ISO 534	μm	73	80	92	104	120	139	168	215
Volume specifico Bulk	ISO 534	cm ³ /g	0.81	0.8	0.8	0.8	0.8	0.82	0.84	0.86
Liscio Bekk Smoothness Bekk	ISO 5627	s	500	500	500	450	400	350	300	200
Lucido Gardner Gloss Gardner	ISO 8254-1	%	40 max	40 max	45 max	45 max	45 max	45 max	45 max	45 max
Grado di bianco CIE Whiteness CIE	ISO 11475	%	122	122	122	122	122	122	122	122
Bianco ISO Brightness ISO	ISO 2470 (D65)	%	97	97	97	97	97	97	97	97
Opacità ISO Opacity ISO	ISO 2471	%	92.5	94	95	96	97	98	98 min	98 min

Finitura *Finishing*

Satin

Tipo di stampa *Printing methods*

Sheet-fed offset

Applicazioni *End uses*

Brochure, Calendari, Copertine di libri e di riviste, Libri d'arte e di lusso, Libri illustrati, Libri per bambini, Locandine, Report ambientali, Report commerciali e finanziari, Stampe commerciali

Brochures, Calendars, Books and publishing covers, Art and luxury books, Illustrated books, Children books, Posters, Environmental reports, Business and financial reports, Commercial printing

I valori relativi ai singoli prodotti sono forniti a titolo esemplificativo e possono essere soggetti a modifiche senza preavviso. Ogni valore è soggetto a determinate tolleranze.
Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

BURGO
GROUP